

AM

## PATENT ABSTRACTS OF JAPAN

(11)Publication number : 05-058786

(43)Date of publication of application : 09.03.1993

(51)Int.Cl.

C30B 29/04

C01B 31/06

(21)Application number : 03-244924

(71)Applicant : SUMITOMO ELECTRIC IND LTD

(22)Date of filing : 29.08.1991

(72)Inventor : SATO SHUICHI  
SUMIYA HITOSHI  
GODA YASUSHI

## (54) METHOD FOR SYNTHESIZING DIAMOND

## (57)Abstract:

PURPOSE: To remove nitrogen which makes diamond crystals yellowish from a solvent by adding Al, Ti or Zr to the solvent when seed diamond crystals are put in a region in which diamond is stably grown by a temp. difference method in the case of diamond synthesis with the seed crystals as nuclei by diffusing carbon from a carbon source fed through the solvent and to inhibit the intrusion of carbide and nitride into diamond crystals, since the deterioration of the quality of synthesized diamond due to the intrusion is occurred in the case when Ti or Zr is added.

CONSTITUTION: An element forming nitride and carbide at the same time is added as a nitrogen getter to a solvent. The element has lower viscosity than the solvent. Nitride and carbide formed before the growth of diamond crystals are allowed to float or settle.

## LEGAL STATUS

[Date of request for examination]

28.01.1998

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

3205970

[Date of registration]

06.07.2001

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office

USPS EXPRESS MAIL

ED 636 851 893 US

MAR 17 2006